

# STAREX SD-0170

ABS hohe Schlagzähigkeit

Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,04
	Melt Flow Index	220°C, 10kg	ISO 1133	g/10min	11,5
Thermal	Heat Deflection Temperature (unannealed)	1.8 MPa, 4.0mm	ISO 75-2	°C	78
	Heat Deflection Temperature (unannealed)	0.45 MPa, 4.0mm	ISO 75-2	°C	90
	Heat Deflection Temperature (annealing)	1.8 MPa, 4.0mm	ISO 75-2	°C	97
	Heat Deflection Temperature (annealing)	0.45 MPa, 4.0mm	ISO 75-2	°C	101
	Vicat Softening Temperature	B/50	ISO R 306	°C	94
	Vicat Softening Temperature	B/120	ISO R 306	°C	97
Mechanical	Tensile Strength at Yield	50mm/min	ISO 527	MPa	35
	Tensile Strain at Break	50mm/min	ISO 527	%	12
	Tensile Modulus	50mm/min	ISO 527	MPa	2000
	Tensile Strength at Break	50mm/min	ISO 527	MPa	30
	Flexural Strength	2mm/min	ISO 178	MPa	52
	Flexural Modulus	2mm/min	ISO 178	MPa	1700
	Izod Impact Strength (notched)	at 23°C, 4mm	ISO 180 1A	KJ/m <sup>2</sup>	35
	Charpy Impact Strength (V-notched)	23°C, 4mm	ISO 179 1eA	KJ/m <sup>2</sup>	35
	Rockwell Hardness	R-scale	ISO 2039-2	-	95

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.



Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information returns the result of the quality inspection. An assurance of certain properties and qualities for specific uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.